

Please amend the Application as follows.


Amendments to the claims:


The following claim listing will replace all previous listings in the application:

1. (Currently amended) Process for the optical writing of optically readable digital information in a two-dimensional extended storage medium, characterised in ~~that~~wherein on account of the optical writing process the surface topography of the storage medium is suitable ~~and sufficiently modified~~ for the optical reading process, and is sufficiently modified so that a depression of at least 10 nm and a width, measured on the original surface, of less than 10 µm is achieved in one direction more specifically without substantial portions of the detected signal resulting from a degradation and/or a physical or chemical modification of the areas adjacent to the absorber layer,

wherein the writing is carried out using laser light with an energy density of a light pulse between 10 mJ/cm² and 100 mJ/cm² and with an intensity of between 0.15 mW and 100 mW, and

wherein as light-active polymer films side-chain polymers, optionally block polymers and/or graft polymers are used, to which dyes are bound as side chains via a STQ-spacer (formula I) and dimensionally anisotropic groups are likewise bound via a STQ-spacer (formula II), wherein formula I has the structure





in which


y denotes 1 or 2,

z denotes 0, 1 or 2 and

$X^{2'}$ and Ar^2 and/or $X^{3'}$ and Ar^3 may have different meanings, if y and/or z denote 2,

A denotes O, S or N-C₁- to C₄-alkyl,

Q^1 denotes -O-, -S-, -(N-R⁵)-, -C(R⁶R⁷)_p-, -(C=O)-, -(O-CO)-, -(NR⁵-CO)-, -(SO₂)-, -(O-SO₂)-, -(NR⁵-SO₂)-, -(C=NR⁸)-, -(CNR⁸-NR⁵)-, -O-C₆H₅-COO- or a bivalent radical of the formula



MO-7059

- 3 -

T¹ denotes -(CH₂)_p-, wherein the chain may be interrupted by -O-, -NR⁹-, or -OSiR¹⁰₂O- and may be substituted by methyl,

S¹ denotes a direct bond, -O-, -S- or -NR⁹-,

P denotes an integer from 2 to 12, preferably 2 to 8, in particular 2 to 4,

R⁹ denotes hydrogen, methyl, ethyl, or propyl,

R¹⁰ denotes methyl or ethyl,

R¹¹ to R²² independently of one another denote hydrogen or a non-ionic substituent,

X⁴ denotes hydrogen, halogen, cyano, nitro, CF₃, CCl₃, -COO-C₁- to C₄- alkyl or X^{4'}-R⁴,


X^{1'}, X^{2'}, X^{3'} and X^{4'} denote a direct bond, -O-, -S-, -(N-R⁵)-, -C(R⁶R⁷)-, -(C=O)-, -(CO-O)-, -(CO-NR⁵)-, -(SO₂)-, -(SO₂-O)-, (SO₂-NR⁵)-, or -(CNR⁸-NR⁵)- and

X^{2'} and X^{3'} may in addition denote -(C=NR⁸)-, -(N=N)- and at least one of the groups X^{2'} or X^{3'} denotes -N=N-,

R⁴, R⁵, R⁶, R⁷ and R⁸ independently of one another denote hydrogen, C₁- to C₄- alkyl, or C₆- to C₁₀-aryl and

R⁴ and R⁵ in addition independently of one another denote C₁- to C₂₀-alkyl-(C=O)-, C₃- to C₁₀-cycloalkyl-(C=O)-, C₂- to C₂₀-alkenyl-(C=O)-, C₆- to C₁₀-aryl-(C=O), C₁- to C₂₀-alkyl-(SO₂)-, C₃- to C₁₀-cycloalkyl-(SO₂), C₂- to C₂₀-alkenyl-(SO₂)- or C₆- to C₁₀-aryl-(SO₂), wherein


by the term non-ionic substituents are understood halogen, cyano, nitro, C₁- to C₂₀-alkyl, C₁- to C₂₀-alkoxy, phenoxy, C₃- to C₁₀-cycloalkyl, C₂- to C₂₀-alkenyl, C₆- to C₁₀-aryl, C₁- to C₂₀-alkyl-(C=O)-, C₆- to C₁₀-aryl-(C=O)-, C₁- to C₂₀-alkyl-(SO₂)-, C₁- C₂₀-alkyl-(C=O)-O-, C₁- to C₂₀-alkyl-(C=O)-NH-, C₆- to C₁₀-aryl-(C=O)-NH-, C₁- to C₂₀-alkyl-O-(C=O)-, C₁- to C₂₀-alkyl-NH-(C=O)-, C₆ to C₁₀-aryl-NH-(C=O)- or a radical of the formula



and the alkyl, cycloalkyl, alkenyl and aryl radicals in turn may be substituted by up to 3 radicals from the group comprising halogen, cyano, nitro, C₁- to C₂₀-alkyl, C₁- to C₂₀-alkoxy, C₃- to C₁₀-cycloalkyl, C₂- to C₂₀-alkenyl or C₆- to C₁₀-aryl, and the alkyl and alkenyl radicals may be straight-chain or branched, and

by the term halogen is understood fluorine, chlorine, bromine and iodine, in particular fluorine and chlorine,

and formula II is described by



wherein the above substituent definitions (formula I) are also valid for formula II, with the proviso that none of the groups X² or X³ may denote -N=N- and R¹¹ to R²² may not denote a radical of the formula (VIII).

2. (Currently amended) Process according to claim 1, characterised in that wherein polymer films are used as storage medium.

3. (Currently amended) Process according to claim 1, ~~characterised in that~~wherein a multi-layer disk is used as storage medium, which comprises at least one mechanically sufficiently stable substrate, at least one polymer film forming the light-active layer, and a covering layer.

4. (Currently amended) Process according to Claim 1, in which a storage medium is used and the light-active layer predominantly comprises oligomers and/or polymers containing dyes that orientate under the action of light, ~~preferably amorphous polymers, particularly preferably side group polymers.~~

5. (Currently amended) Process according to Claim 3, ~~characterised in that~~wherein a polymer film whose mass density is closely matched to that of the light-active layer is used as covering layer.

6. (Canceled)

7. (Currently amended) Process according to claim 1, ~~characterised in that~~wherein the dye side groups I are used, wherein substituents and formulae have the meanings defined in claim 1, and in addition

Ar¹ denotes a radical of the formula (III),

Ar² denotes a radical of the formula (VI),

Ar³ denotes a radical of the formula (VII) or (V),


y denotes 1 or 2,

z denotes 0, 1 or 2 and

X^{2'} and Ar² and X^{3'} and Ar³ may have different meanings if y and/or z denote 2,

A denotes O or S,

Q¹ denotes -O-, -(N-R⁵)-, -(C=O)-, -(O-CO)-, -(NR⁵-CO)-, -(SO₂)-, -(O-SO₂)-, -(NR⁵-SO₂)-, -O-C₆H₅-COO- or a bivalent radical of the formula



T¹ denotes -(CH₂)_p- wherein the chain may be interrupted by -O-, -NR⁹-, or -OSiR¹⁰₂O- and may be substituted by methyl,


S¹ denotes a direct bond, -O-, -S-, or -NR⁹-

p denotes an integer from 2 to 8, in particular 2 to 4,

R⁹ denotes hydrogen, methyl or ethyl,

R¹⁰ denotes methyl or ethyl,

R¹¹ to R²² independently of one another denote hydrogen, halogen, cyano, nitro, C₁- to C₂₀-alkyl, C₁- to C₂₀-alkoxy, phenoxy, C₃- to C₁₀-cycloalkyl, C₂- to C₂₀-alkenyl, C₆- to C₁₀-aryl, C₁- to C₂₀-alkyl-(C=O)-, C₆- to C₁₀-aryl-(C=O)-, C₁- to C₂₀-alkyl-(SO₂)-, C₁- to C₂₀-alkyl-(C=O)-O-, C₁- to C₂₀-alkyl-(C=O)-NH-, C₆- to C₁₀-aryl-(C=O)-NH-, C₁- to C₂₀-alkyl-O-(C=O)-, C₁- to C₂₀-alkyl-NH-(C=O)-, C₆- to C₁₀-aryl-NH-(C=O)- or a radical of the formula



X^4 denotes hydrogen, halogen, cyano, nitro, CF_3 , CCl_3 , $-COO-C_1$ to C_4 -alkyl or $X^{4'}$ - R^4 ,

$X^{1'}$, $X^{2'}$, $X^{3'}$ and $X^{4'}$ denote a direct bond, $-O-$, $-(N-R^5)-$, $-C(R^6R^7)-$, $-(C=O)-$, $-(CO-O)-$, $-(CO-NR^5)-$, $-(SO_2)-$ or $(SO_2-O)-$ and

$X^{2'}$ and $X^{3'}$ may in addition denote $-(N=N)-$ and at least one of the groups $X^{2'}$ or $X^{3'}$ denotes $-N=N-$,

R^4 , R^5 , R^6 , R^7 and R^8 independently of one another denote hydrogen, C_1 - to C_4 -alkyl, or C_6 - to C_{10} -aryl and

R^4 and R^5 in addition independently of one another denote C_1 - to C_{20} -alkyl- $(C=O)-$, C_3 - to C_{10} -cycloalkyl- $(C=O)-$, C_2 - to C_{20} -alkenyl- $(C=O)-$, C_6 - to C_{10} -aryl- $(C=O)-$, C_1 - to C_{20} -alkyl- $(SO_2)-$, C_3 - to C_{10} -cycloalkyl- $(SO_2)-$, C_2 - to C_{20} -alkenyl- $(SO_2)-$, or C_6 - to C_{10} -aryl- $(SO_2)-$.

and dimensionally anisotropic side groups II are used wherein substituents and formula have the meanings defined in claim 1, and in addition

Ar^1 denotes a radical of the formula (III),

Ar^2 denotes a radical of the formula (VI),

Ar^3 denotes a radical of the formulae (VII) or (V),

y denotes 1 or 2,

z denotes 0, 1 or 2 and

$X^{2'}$ and Ar^2 and/or $X^{3'}$ and Ar^3 may have different meanings if y and/or z denote 2,

A denotes O or S,

Q^1 denotes -O-, -(N-R⁵)-, -(C=O)-, -(O-CO)-, -(NR⁵-CO)-, -(SO₂)-, -(O-SO₂)-, -(NR⁵-SO₂)-, -O-C₆H₅-COO- or a bivalent radical of the formula



T^1 denotes -(CH₂)_p-, wherein the chain may be interrupted by -O-, -NR⁹-, or -OSiR¹⁰₂O- and may be substituted by methyl,

S^1 denotes a direct bond, -O-, -S-, or -NR⁹-

p denotes an integer from 2 to 8, in particular 2 to 4,

R⁹ denotes hydrogen, methyl or ethyl,

R¹⁰ denotes methyl or ethyl,

R¹¹ to R²² independently of one another denote hydrogen, halogen, cyano, nitro, C₁- to C₂₀-alkyl, C₁- to C₂₀-alkoxy, phenoxy, C₃- to C₁₀-cycloalkyl, C₂- to C₂₀-alkenyl, C₆- to C₁₀-aryl, C₁- to C₂₀-alkyl-(C=O)-, C₆- to C₁₀-aryl-(C=O)-, C₁- to C₂₀-alkyl-(SO₂)-, C₁- to C₂₀-alkyl-(C=O)-O-, C₁- to C₂₀-alkyl-(C=O)-NH-, C₆- to C₁₀-aryl-(C=O)-NH-, C₁- to C₂₀-alkyl-O-(C=O), C₁- to C₂₀-alkyl-NH-(C=O)-, or C₆- to C₁₀-aryl-NH-(C=O)-,

X^4 denotes hydrogen, halogen, cyano, nitro, CF₃, CCl₃, -COO-C₁ to C₄-alkyl or $X^{4'}$ -R⁴,

X^{1'}, X^{2'}, X^{3'} and X^{4'} denote a direct bond, -O-, -(N-R⁵)-, -C(R⁶R⁷)-, -(C=O)-, -(CO-O)-, -(CO-NR⁵)-, -(SO₂)- or (SO₂-O)- and

R⁴, R⁵, R⁶, R⁷ and R⁸ independently of one another denote hydrogen, C₁- to C₄-alkyl, or C₆- to C₁₀-aryl and

R⁴ and R⁵ in addition independently of one another denote C₁- to C₂₀-alkyl-(C=O)-, C₃- to C₁₀-cycloalkyl-(C=O)-, C₂- to C₂₀-alkenyl-(C=O)-, C₆- to C₁₀-aryl-(C=O)-, C₁- to C₂₀-alkyl-(SO₂)-, C₃- to C₁₀-cycloalkyl-(SO₂)-, C₂- to C₂₀-alkenyl-(SO₂)-, or C₆- to C₁₀-aryl-(SO₂)-.

8. (Previously presented) Process according to Claim 1, wherein the storage medium on which information is to be written has a light-active layer of a thickness between 0.05 and 1000 µm.

9. (Previously presented) Process according to Claim 1, wherein the storage medium that is used has an optical density at the wavelength of the writing laser of the light-active layer of between 0.3 and 20.

10. (Canceled)

11. (Canceled).

12. (Currently amended) Process according to Claim 1, ~~characterised in that~~ wherein the change in the surface topography of the storage medium is produced by laser light, ~~preferably~~ having wavelengths between 380 nm and 820 nm.

13. (Currently amended) Process according to Claim 1, ~~characterised in that~~ wherein the light has an intensity of between 150 µW and 100 mW and is focused on spots having a dimension (full half-value width) in a range between 10 nm and 8 µm.

14. (Currently amended) Process according to Claim 1, characterised in that ~~wherein~~ information can be written on storage media whose carrier layer comprises a polymer, ~~preferably a thermoplastic polymer, particularly preferably polycarbonate.~~


15. (Currently amended) Process according to Claim 1, characterised in that a signal deviation is written in the storage medium having at least a carrier/noise ratio of 20 dB.

16. (Currently amended) Process according to Claim 1, wherein information can be written on storage media that contain, between the light active dye-containing layer and the covering layer, an additional, light-reflecting layer, ~~preferably selected from the group consisting of metals comprising aluminum, silver, and gold, particularly preferably from the group comprising aluminium and silver, and most particularly preferably aluminium.~~


17. (Previously presented) Process according to Claim 1, wherein the storage medium on which information is to be written has no reflecting layer.

18. (Currently amended) Process according to Claim 1, characterised in that the optical writing process is performed with polarised light of variable intensity, produced by a laser with an acousto-optical modulator or by modulation of a laser diode, and the polarisation state of the reflected light is detected in a polarisation optics system.

19. (Withdrawn) Monomers of the formula




wherein R^1 denotes hydrogen or methyl and
 the other radicals have the meanings defined in claim 6, and
 $-(X^3-Ar^3)_z-X^4$ denotes a radical of the formula



X^3 denotes $-N=N-$ or $-CO-NH-$.


20. (Withdrawn) Monomers of the formula (Ia) according to claim 19, wherein
 $-(X^3-Ar^3)_z-X^4$ denotes a radical of the formula



X^3 denotes $-O-$, $-(SO_2)-$, $-(C=O)-$, $-(N-R^5)-$, $-(CO-NR^5)-$ or $-C(R^6R^7)-$.


21. (Withdrawn) Monomers of the formula (Ia) according to claim 19, wherein

$-(X^2-Ar^2)_y-$ denotes a bivalent radical of the formula




22. (Withdrawn) Monomers of the formula (Ia) according to claim 19, wherein

$-(X^1-Ar^1)-X^2-$ denotes a bivalent radical of the formula



wherein X^1 and X^2 are in the m- or p-position relative to one another and X^1 and the azo group are in the o- or p-position relative to one another.

23. (Withdrawn) Monomers of the formula




MO-7059

- 13 -

$X^{2'}$ denotes $-N=N-$ or $-CO-NH-$,

X^4 denotes hydrogen, C_1- to C_4- alkoxy, Di- C_1- to C_4- alkylamino, C_1- , to C_4- alkanoylamino, benzoylamino, cyano or nitro, wherein X^4 is particularly preferably in the p-position to the azo group,

R^{15} to R^{22} independently of one another denote hydrogen, methyl, methoxy or cyano, wherein one of the radicals R^{19} to R^{22} may denote a radical of the formula




which is particularly preferably in the m- or p-position relative to the azo group, in which

$X^{4''}$ denotes hydrogen, C_1- to C_4- alkoxy, Di- C_1- to C_4- alkylamino, C_1- to C_4- alkanoylamino, benzoylamino, cyano or nitro and

$R^{19'}$ to $R^{22'}$ independently of one another denote hydrogen, methyl, methoxy or cyano.


24. (Withdrawn) Polymers produced from monomers according to one or more of the preceding claims.
25. (Canceled)
26. (Canceled)

27. (Withdrawn) Monomers of the formula



wherein R^1 denotes hydrogen or methyl and the other radicals have the meanings as defined in Claim 7, and

$-(X^{3'}-Ar^3)_z-X^4$ denotes radicals of the formula



and $X^{3'}$ denotes $-N=N-$ or $-CO-NH-$.

28. (Withdrawn) A method of using the monomers of claim 19 comprising producing an optical storage medium.

29. (Previously presented) The storage medium prepared by the method of Claim 18.